

# Product specification

Product name	Magnetic Bar 20mmX20mmX300mm			
Item	Name	Symbol	SI	CGS
Shape	Diameter	d	10 mm	1 cm
	Lengh	L	300 mm	30 cm
	Width	W	20 mm	2 cm
	Screw	M	6 mm	0.6 cm
	Direction of magnetization	M	Assiale	
	Surface treatment	Polish	- $\mu$ m	
Measuring point	Surface flux density	B	1100 mT	11000 G
	Attractive force	F	- kgf	- gf
	Magnetic flux density on load point	Bd	- mT	- G
	Total flux	Dia o	- Wb	- Mx
	Permeance coefficient	Pc	- Pc	-
	Operationg temperature range	Tw	100 deg C	212 deg F
	Operationg temperature range	Tw	- deg C	- deg F
Material characteristics	Material grade	Magnetic Bar	304	
	Remanence	Br	- mT	- kG
	Coeritive forces	Hcb	- kA/m	- kOe
	Intrinsic coercivity	Hcj	- kA/m	- kOe
	Maximum energy product	BH	- kJ/m3	- MGOe
	Temperature coefficient	Br	- %/deg C	- %/deg F
		Hcj	- %/deg C	- %/deg F
	Max. operating temperature	Tw	- deg C	- deg F
	Curie temperature	Tc	- deg C	- deg F
	Density	P	- kg/m3	-
	Weight	Net	0.9 kg	900 g
Remark	REACH RoHS Directive			

Information on these magnetic characteristics are approximate and reference values. When using the calculated values for actual magnetic application products and research and development of the application of magnetic products, use these values as reference values. We are not responsible for the results from the reference values. The details can be found by referring to the product specifications. All specifications are subject to change without notice.