

Product specification

| Product name | Neodymium Dia13mmX5mm | | | | |
|--------------------------|-------------------------------------|-----------|------------|---------|---------------|
| Item | Name | Symbol | SI | | CGS |
| Shape | Diameter | D | 13 | mm | 1.3 cm |
| | Height | H | 5 | mm | 0.5 cm |
| | Dimensional tolerance +/- | D | 0.1 | mm | 0.01 cm |
| | | H | 0.1 | mm | 0.01 cm |
| | Direction of magnetization | M | Assiale | | |
| Measuring point | Surface treatment | Ni | 12 | μm | |
| | Surface flux density | B | 347.2 | mT | 3472 G |
| | Attractive force | F | 2.71 | kgf | 2711 gf |
| | Magnetic flux density on load point | Bd | 589.8 | mT | 5898 G |
| | Total flux | Dia o | 0.00007828 | Wb | 7828 Mx |
| | Permeance coefficient | Pc | 1.02 | Pc | - |
| | Operating temperature range | Tw | 90 | deg C | 194 deg F |
| Material characteristics | Operating temperature range | Tw | - | deg C | - deg F |
| | Material grade | Neodymium | 35 | | |
| | Remanence | Br | 1170-1220 | mT | 11.7-12.2 kG |
| | Coercive forces | Hcb | >868 | kA/m | >10.9 kOe |
| | Intrinsic coercivity | Hcj | >955 | kA/m | >12 kOe |
| | Maximum energy product | BH | 263-287 | kJ/m3 | 33-36 MGOe |
| | Temperature coefficient | Br | -0.12 | %/deg C | 31.78 %/deg F |
| | | Hcj | -0.55 | %/deg C | 31.01 %/deg F |
| | Max. operating temperature | Tw | <80 | deg C | <176 deg F |
| | Curie temperature | Tc | 310 | deg C | 590 deg F |
| | Density | P | 7.5 | kg/m3 | - |
| | Weight | Net | 0.00497 | kg | 4.97 g |
| Remark | REACH RoHS Directive | | | | |

Information on these magnetic characteristics are approximate and reference values. When using the calculated values for actual magnetic application products and research and development of the application of magnetic products, use these values as reference values. We are not responsible for the results from the reference values. The details can be found by referring to the product specifications. All specifications are subject to change without notice.