Product specification

Product name	Samarium Cobalt 20mmX10mmX5mm					
Item	Name	Symbol	SI		CGS	
Shape	Lengh	L	20	mm	2	cm
	Width	W	10	mm	1	cm
	Height	H	5	mm	0.5	cm
	Dimensional tolerance +/-	L	0.1	mm	0.01	cm
		W	0.1	mm	0.01	cm
		H	0.1	mm	0.01	cm
	Direction of magnetization	M	Assiale			
	Surface treatment	-	-	μm		
Measuring point	Surface flux density	B	288	mT	2880	G
	Attractive force	F	3.27	kgf	3273	gf
	Magnetic flux density on load point	Bd	456	mT	4560	G
	Total flux	Dia o	0.0000912	Wb	9120	Mx
	Permeance coefficient	Pc	0.8	Pc	-	
	Operationg temperature range	Tw	320	deg C	608	deg F
	Operationg temperature range	Tw	-	deg C	-	deg F
Material characteristics	Material grade	Samarium Cobalt	YXG28			
	Remanence	Br	1030-1080	mT	10.3-10.8	kG
	Coericive forces	Hcb	756-796	kA/m	9.5-10.0	kOe
	Intrisic coercivity	Hcj	>1433	kA/m	>18	kOe
	Maximum energy product	BH	207-220	kJ/m3	26-28	MGOe
	Temperature coefficient	Br	-0.035	%/deg C	31.94	%/deg F
		Hcj	-0.2	%/deg C	31.64	%/deg F
	Max. operating temperature	Tw	300	deg C	572	deg F
	Curie temperature	Tc	800	deg C	1472	deg F
	Density	P	8.5	kg/m3	-	
	Weight	Net	0.0085	kg	8.5	g
Remark	REACH RoHS Directive					

Information on these magnetic characteristics are approximate and reference values. When using the calculated values for actual magnetic application products and research and development of the application of magnetic products, use these values as reference values. We are not responsible for the results from the reference values. The details can be found by referring to the product specifications. All specifications are subject to change without notice.

Copyright © 2000-2026 Magfine Corporation All Rights Reserved.