Product specification

Product name	Samarium Cobalt 30mmX10mmX3mm					
Item	Name	Symbol	SI		CGS	
Shape	Lengh	L	30	mm	3	cm
	Width	W	10	mm	1	cm
	Height	H	3	mm	0.3	cm
	Dimensional tolerance +/-	L	0.1	mm	0.01	cm
		W	0.1	mm	0.01	cm
		H	0.1	mm	0.01	cm
	Direction of magnetization	M	Assiale			
	Surface treatment	-	-	μm		
Measuring point	Surface flux density	B	190.1	mT	1901	G
	Attractive force	F	3.83	kgf	3833	gf
	Magnetic flux density on load point	Bd	264.3	mT	2643	G
	Total flux	Dia o	0.0000793	Wb	7930	Mx
	Permeance coefficient	Pc	0.35	Pc	-	
	Operationg temperature range	Tw	270	deg C	518	deg F
	Operationg temperature range	Tw	-	deg C	-	deg F
Material characteristics	Material grade	Samarium Cobalt	YXG28H			
	Remanence	Br	1030-1080	mT	10.3-10.8	kG
	Coericive forces	Hcb	756-796	kA/m	9.5-10.0	kOe
	Intrisic coercivity	Hcj	>1990	kA/m	>25	kOe
	Maximum energy product	BH	207-220	kJ/m3	26-28	MGOe
	Temperature coefficient	Br	-0.035	%/deg C	31.94	%/deg F
		Hcj	-0.2	%/deg C	31.64	%/deg F
	Max. operating temperature	Tw	350	deg C	662	deg F
	Curie temperature	Tc	800	deg C	1472	deg F
	Density	P	8.5	kg/m3	-	
	Weight	Net	0.00765	kg	7.65	g
Remark	REACH RoHS Directive					

Information on these magnetic characteristics are approximate and reference values. When using the calculated values for actual magnetic application products and research and development of the application of magnetic products, use these values as reference values. We are not responsible for the results from the reference values. The details can be found by referring to the product specifications. All specifications are subject to change without notice.

Copyright © 2000-2026 Magfine Corporation All Rights Reserved.