

Product specification

| Product name | Lifter CSYQ300A | | | |
|--------------------------|-------------------------------------|--------|-----------|-----------|
| Item | Name | Symbol | SI | CGS |
| Shape | Radian | R | 155 mm | 15.5 cm |
| | Lengh | L | 162 mm | 16.2 cm |
| | Width | W | 92 mm | 9.2 cm |
| | Height | H | 91 mm | 9.1 cm |
| | Direction of magnetization | M | Assiale | |
| | Surface treatment | - | - μ m | |
| Measuring point | Surface flux density | B | - mT | - G |
| | Attractive force | F | 300 kgf | 300000 gf |
| | Magnetic flux density on load point | Bd | - mT | - G |
| | Total flux | Dia o | - Wb | - Mx |
| | Permeance coefficient | Pc | - Pc | - |
| | Operating temperature range | Tw | - deg C | - deg F |
| | Operating temperature range | Tw | - deg C | - deg F |
| Material characteristics | Material grade | Lifter | Alnico5 | |
| | Remanence | Br | - mT | - kG |
| | Coeritive forces | Hcb | - kA/m | - kOe |
| | Intrinsic coercivity | Hcj | - kA/m | - kOe |
| | Maximum energy product | BH | - kJ/m3 | - MGOe |
| | Temperature coefficient | Br | - %/deg C | - %/deg F |
| | | Hcj | - %/deg C | - %/deg F |
| | Max. operating temperature | Tw | - deg C | - deg F |
| | Curie temperature | Tc | - deg C | - deg F |
| | Density | P | - kg/m3 | - |
| | Weight | Net | 7.5 kg | 7500 g |
| Remark | - | | | |

Information on these magnetic characteristics are approximate and reference values. When using the calculated values for actual magnetic application products and research and development of the application of magnetic products, use these values as reference values. We are not responsible for the results from the reference values. The details can be found by referring to the product specifications. All specifications are subject to change without notice.