Product specification

Product name	Colour Magnet Dia13mmX6mm Orange					
ltem	Name	Symbol	SI		CGS	
Shape	Diameter	D	13	mm	1.3	cm
	Height	Н	6	mm	0.6	cm
	Direction of magnetization	М	Assiale			
	Surface treatment	Nylon	500	μm		
Measuring point	Surface flux density	В	132.2	mT	1322	G
	Attractive force	F	-	kgf	-	gf
	Magnetic flux density on load point	Bd	214.2	mT	2142	G
	Total flux	Dia o	0.0000284	Wb	2844	Mx
	Permeance coefficient	Pc	1.28	Pc	-	
	Operationg temperature range	Tw	-	deg C	-	deg F
	Operationg temperature range	Tw	-	deg C	-	deg F
Material characteristics	Material grade	Colour Magnet	Y30			
	Remanence	Br	380-420	mT	3.8-4.2	kG
	Coericive forces	Hcb	160-216	kA/m	2.0-2.7	kOe
	Intrisic coercivity	Hcj	-	kA/m	-	kOe
	Maximum energy product	ВН	26.3-29.5	kJ/m3	3.3-3.7	MGOe
	Temperature	Br	-0.18	%/deg C	31.68	%/deg F
	coefficient	Hcj	-	%/deg C	-	%/deg F
	Max. operating temperature	Tw	<200	deg C	<392	deg F
	Curie temperature	Tc	460	deg C	860	deg F
	Density	Р	-	kg/m3	-	-
	Weight	Net	0.00398	kg	3.98	g
Remark	REACH RoHS Directive					

Information on these magnetic characteristics are approximate and reference values. When using the calculated values for actual magnetic application products and research and development of the application of magnetic products, use these values as reference values. We are not responsible for the results from the reference values. The details can be found by referring to the product specifications. All specifications are subject to change without notice.