

Product specification

| | | | | |
|--------------------------|-------------------------------------|---------------|-----------------|---------------|
| Product name | Colour Magnet Dia24.6mmX7mm Red | | | |
| Item | Name | Symbol | SI | CGS |
| Shape | Diameter | D | 24.6 mm | 2.46 cm |
| | Height | H | 7 mm | 0.7 cm |
| | Direction of magnetization | M | Assiale | |
| | Surface treatment | Nylon | 500 μ m | |
| Measuring point | Surface flux density | B | 96.4 mT | 964 G |
| | Attractive force | F | - kgf | - gf |
| | Magnetic flux density on load point | Bd | 157.7 mT | 1577 G |
| | Total flux | Dia o | 0.0000749 6 Wb | 7496 Mx |
| | Permeance coefficient | Pc | 0.71 Pc | - |
| | Operationg temperature range | Tw | - deg C | - deg F |
| | Operationg temperature range | Tw | - deg C | - deg F |
| | Material grade | Colour Magnet | Y30 | |
| Material characteristics | Remanence | Br | 380-420 mT | 3.8-4.2 kG |
| | Coericive forces | Hcb | 160-216 kA/m | 2.0-2.7 kOe |
| | Intrinsic coercivity | Hcj | - kA/m | - kOe |
| | Maximum energy product | BH | 26.3-29.5 kJ/m3 | 3.3-3.7 MGOe |
| | Temperature coefficient | Br | -0.18 %/deg C | 31.68 %/deg F |
| | | Hcj | - %/deg C | - %/deg F |
| | Max. operating temperature | Tw | <200 deg C | <392 deg F |
| | Curie temperature | Tc | 460 deg C | 860 deg F |
| | Density | P | - kg/m3 | - |
| | Weight | Net | 0.0166 kg | 16.6 g |
| Remark | REACH RoHS Directive | | | |

Information on these magnetic characteristics are approximate and reference values. When using the calculated values for actual magnetic application products and research and development of the application of magnetic products, use these values as reference values. We are not responsible for the results from the reference values. The details can be found by referring to the product specifications. All specifications are subject to change without notice.